



ProLift 3.5 system is a hydrophobic/hydro-insensitive, plural component polymeric MDI based polymer system designed for concrete lifting/leveling, joint matching, void filling and concrete undersealing in wet environments. This System has been specially formulated for exceptional flow or spread under concrete road or slab section (s) when water is present.

### Typical Properties of Components

Component	B-Prolift-3.5	A-Prolift-3.5
Appearance	Transparent Black liquid	Transparent Brown liquid
Viscosity	500 cps at 72°F	200 cps at 72°F
Specific Gravity	1.07	1.24
Storage Temperature	50°F-100°F	50°F-110°F

### Mix Ratio

By weight.....100 parts poly : 116 parts iso  
 By volume.....100 parts poly : 100 parts iso

### Typical Properties of Hand-Mixed System at 72°F and thru HPIM equipment

	at 72°F	at 120°F
Cream Time	22 seconds	7 seconds
Tack Free Time	60 seconds	14 seconds
Rise Time	90 seconds	15 seconds
Free Rise Core Density	4 pcf	3 – 4 pcf

### Process Parameters

Iso Temperature	100°F to 130°F
Poly Temperature	100°F to 130°F
Mixing Pressure	Minimum 800 static, 600 dynamic psi, 1000/800 preferred

### Typical Foam Physical Properties

In-Place Density (ASTM D-1622)	3 - 4 pcf		
Compressive Strength (ASTM D-1621), parallel to rise	80 - 100 psi		
Elastic Modulus of Compression, (ASTM D-1621)	2400 – 3200 psi		
Tensile Strength (ASTM D-1623), parallel to rise	100 – 120 psi		
Closed cell content, ASTM D-6226	> 92%		
Water Absorption (ASTM D-2842)	< 0.04 lbs/ft <sup>2</sup>		
NYDOT Hydro-Insensitivity test, GTP-9	> 96% density retention		
	> 93% comp str retention		
Dimensional stability, % volume change (ASTM D-2126)			
	Heat age at 158°F	Freezer at -20°F	Humid age at 100%RH & 120°F
28 day aging	-1.5%	-0.1%	-1.0%
Resistance to Solvents	Excellent		
Resistance to Mold and Mildew	Excellent		
Maximum service temperature	200°F		

## Storage and Handling

---

Store the poly from 50°F to 100°F. Avoid moisture contamination during storage, handling, and processing. For both components, pad containers and day tanks with either nitrogen or dry air (desiccant cartridge or air dryer @ -40°F dew point). For optimum shelf life, the recommended storage temperature for iso is 50°F to 110°F. Do not expose iso to lower temperatures – freezing may occur. Shelf life is 6 months for factory sealed containers. To insure handling safety, consult the Safety Data Sheets associated with this product.

## Application Cautions

---

Careful consideration should be given to selection and application of any Polysource Industries Inc. foam system, including injection under concrete slabs and/or into void areas (cavities), where excessive foam mass build-up can occur. Excessive polyurethane foam lift thickness will result in high internal temperatures within the injected foam. These high temperatures can result in degraded foam properties, or in extreme cases, spontaneous combustion. Single lift thickness should be limited to a maximum of 6 inches, allowing at least 15 minutes before an additional lift. Please consult Polysource Industries Inc. for safety considerations, polyurethane system selection and application recommendations.

Polyurethane products manufactured or produced from this liquid system may present a serious fire hazard if improperly used or allowed to remain exposed or unprotected. The character and magnitude of any such hazard will depend on a broad range of factors which are controlled and influenced by the manufacturing and production process, by the mode of application or installation and by the function and usage of the particular product. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions. These ratings are used solely to measure and describe the product's response to heat and flame under controlled laboratory conditions.** Each person, firm or corporation engaged in the manufacture, production, application, installation or use of any polyurethane product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures.

Original: 04/2002  
Revision #8: 05/2018

The Information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the sole responsibility of the user. Polysource Industries Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PSI's direct control. PSI MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.